

IN THE SPECIFICATION:

Please substitute the following paragraph for the paragraph starting at page 6, line 18 and ending at page 7, line 2.

In the method according to the first aspect of the present invention, the resin molding is obtained by mating the convex portion formed in the first molded part with the corresponding ~~the~~ convex portion formed on the second molded part, holding the mated the first and second molded parts by the jig, then connecting the injection nozzle with one end of the through-hole which the other end is in communication with the cavity, injecting the molten resin into the through-hole and the cavity from the injection nozzle, and integrally joining the first and second molded parts, as the resin molding, via the concave and convex portions by the resin.